

COTTON SHIRT (टेरिकटन कमिज)

Details	Specification
a) Color	Color as per Sample of Nepal Police.
b) Fiber Content (Composition of Fabric) <ul style="list-style-type: none"> • Polyester • Cotton 	65 % (± 3) 35 % (± 3)
c) Fabric GSM	147.0 g/m ² (± 5)
d) Construction <ul style="list-style-type: none"> • Warp • Weft 	514 (± 5) per 10cm 370 (± 5) per 10cm
e) Fabric Width <ul style="list-style-type: none"> • Total Width • Cuttable Width 	113 cm (± 2) 111 cm (± 2)
f) Color fastness to washing Warm Water Temperature 40 ⁰ \pm 5 ⁰ cool iron	Min 3
g) Color Fastness to Rubbing <ul style="list-style-type: none"> • Dry • Wet 	Min 4-5 Min 3-4
h) Color Fastness to Light Color Change (after 40 AFU)	Min 2.5
i) Pilling Resistance (Random after 30 minutes)	Min 3.5
j) Tensile Strength <ul style="list-style-type: none"> • Warp • Weft 	Min 500 N Min 340 N
k) Dimensional change after third washing (Hand wash 40 ⁰ c, Line dry cool iron) <ul style="list-style-type: none"> • Warp/Length • Weft/Width 	± 1.0 % ± 1.0 %
l) Tear strength <ul style="list-style-type: none"> • Warp Yarns Torn • Weft Yarns Torn 	Min 28 N Min 27 N
Note: <ol style="list-style-type: none"> 1. Must be a pass report. 2. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. 3. Report must be from single fabrics. 4. Reports combined tested at different times and different sample will be considered as failure. 5. Test that are not requested would not need any report. 6. Report must be authentic and would be counter checked as Nepal Police's discretion. 7. Any report found fake or is not in the system would be considered as Spam thus failure. <p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

COTTON PANTS (टेरिक्टन पाइन्ट)

Details	Specification
a) Color	Color as per Sample of Nepal Police
b) Fiber content (Composition of fabric) <ul style="list-style-type: none"> • Polyester • Cotton 	67 % (± 3) 33 % (± 3)
c) Fabric GSM	186.0 g/m ² (± 5)
d) Construction <ul style="list-style-type: none"> • Warp • Weft 	414 (± 5) per 10cm 450 (± 5) per 10cm
e) Fabric Width <ul style="list-style-type: none"> • Total Width • Cuttable Width 	148 cm (± 2) 144 cm (± 2)
f) Color fastness to washing: Warm Water Temperature 40 ⁰ \pm 5 ⁰ cool iron	Min 4
g) Color Fastness to Rubbing: <ul style="list-style-type: none"> • Dry • Wet 	Min 4 Min 3-4
h) Color Fastness to Light Color Change (after 40 AFU):	Min 3.5
i) Pilling Resistance (Random after 30minutes):	Min 4
j) Tensile Strength <ul style="list-style-type: none"> • Warp • Weft 	Min 620 N Min 450 N
k) Dimensional change after third washing (Hand wash 40 ⁰ c, Line dry cool iron) <ul style="list-style-type: none"> • Warp/Length • Weft/Width 	± 1.0 % ± 1.0 %
l) Tear strength <ul style="list-style-type: none"> • Warp Yarns Torn • Weft Yarns Torn 	Min 43 N Min 26 N
Note: <ol style="list-style-type: none"> 1. Must be a pass report. 2. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. 3. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. 4. Reports combined tested at different times and different sample will be considered as failure. 5. Test that are not requested would not need any report. 6. Report must be authentic and would be counter checked as Nepal Police's discretion. 7. Any report found fake or is not in the system would be considered as Spam thus failure. 	
<p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed.</p> <p>Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

Woolen shirt (उनी कमिज)

Details	Specification
a) Color	Color as per sample of Nepal Police.
b) Fiber Content (Composition of fabric) <ul style="list-style-type: none"> • Polyester • Wool 	63 % (±3) 37 % (±3)
c) Fabric GSM	249.0 g/m ² (±5)
d) Construction <ul style="list-style-type: none"> • Warp • Weft 	212 (±5) per 10cm 190 (±5) per 10cm
e) Fabric Width <ul style="list-style-type: none"> • Total Width • Cuttable Width 	148 cm (± 2) 144 cm (± 2)
f) Color fastness to washing: Warm Water Temperature 40 ⁰ ± 5 ⁰ cool iron	Min 4-5
g) Color Fastness to Rubbing: <ul style="list-style-type: none"> • Dry • Wet 	Min 4-5 Min 4-5
h) Color Fastness to Light Color Change (after 40 AFU):	Min 3.5
i) Pilling Resistance (Random after 30minutes):	Min 1.5
j) Tensile Strength <ul style="list-style-type: none"> • Warp • Weft 	Min 610 N Min 510 N
k) Dimensional change after third washing (Hand wash 40 ⁰ c, Line dry cool iron) <ul style="list-style-type: none"> • Warp/Length • Weft/Width 	±1.25 % ±1.25 %
l) Tear strength <ul style="list-style-type: none"> • Warp Yarns Torn • Weft Yarns Torn 	Min 48 N Min 48 N
Note: <ol style="list-style-type: none"> 1. Must be a pass report. 2. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. 3. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. 4. Reports combined tested at different times and different sample will be considered as failure. 5. Test that are not requested would not need any report. 6. Report must be authentic and would be counter checked as Nepal Police's discretion. 7. Any report found fake or is not in the system would be considered as Spam thus failure. <p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

WOOLEN PANTS (उनी पाइन्ट)

Details	Specification
a) Color	Color as per Sample of Nepal Police
b) Fiber content (Composition of fabric) <ul style="list-style-type: none"> • Polyester • Wool 	65 % (± 3) 35 % (± 3)
c) Fabric GSM	292 g/m ² (± 5)
d) Construction <ul style="list-style-type: none"> • Warp (per 10 cm) • Weft (per 10 cm) 	366/10 cm (± 5) 242/10 cm (± 5)
e) Fabric Width <ul style="list-style-type: none"> • Total Width • Cuttable Width 	154 cm (± 2) 151 cm (± 2)
f) Color fastness to washing: Warm Water Temperature 40 ⁰ c cool iron	Min 4
g) Color Fastness to Rubbing: <ul style="list-style-type: none"> • Dry • Wet 	Min 4 Min 4
h) Color Fastness to Light Color Change (after 40 AFU):	Min 4
i) Pilling Resistance (Random after 30minutes):	Min 3
j) Tensile Strength <ul style="list-style-type: none"> • Warp • Weft 	Min 1200 N Min 850 N
k) Dimensional change after third washing (Hand wash 40 ⁰ c, Line dry cool iron) <ul style="list-style-type: none"> • Warp/Length • Weft/Width 	± 1.0 % ± 1.0 %
l) Tear strength <ul style="list-style-type: none"> • Warp Yarns Torn • Weft Yarns Torn 	Min 45 N Min 45 N
Note: <ol style="list-style-type: none"> 1. Must be a pass report. 2. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. 3. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. 4. Reports combined tested at different times and different sample will be considered as failure. 5. Test that are not requested would not need any report. 6. Report must be authentic and would be counter checked as Nepal Police's discretion. 7. Any report found fake or is not in the system would be considered as Spam thus failure. <p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

COTTON CHUSTA- Rib stops (चुस्ता)

Details	Specification
(Rib stops Fabric only) Rib stops size:0.7cm	
a) Color	Color as per sample of Nepal Police
b) Fiber Content (Composition of fabric) <ul style="list-style-type: none"> • Cotton • Nylon 	64% (± 3) 36% (± 3)
c) Fabric GSM	244.0 g/m ² (± 5)
d) Construction <ul style="list-style-type: none"> • Warp • Weft 	416 (± 5) per 10cm 224 (± 5) per 10cm
e) Fabric Width <ul style="list-style-type: none"> • Total Width • Cuttable Width 	154 cm (± 2) 152 cm (± 2)
f) Color fastness to washing Warm Water Temperature 40 ⁰ \pm 5 ⁰ cool iron	Min 4-5
g) Color Fastness to Rubbing: <ul style="list-style-type: none"> • Dry • Wet 	Min 4-5 Min 3-4
h) Color Fastness to Light Color change (after 40AFU)	Min 3.5
i) Tensile Strength <ul style="list-style-type: none"> • Warp • Weft 	Min 630 N Min 320 N
j) Dimensional change after third washing (Hand wash 40 ⁰ c, Line dry cool iron) <ul style="list-style-type: none"> • Warp/Length • Weft/Width 	$\pm 1.5\%$ $\pm 1.5\%$
k) Pilling Resistance (Random after 30 minutes)	Min 4-5
l) Tear strength (Elmendorf) <ul style="list-style-type: none"> • Warp Yarns Torn • Weft Yarns Torn 	Min 26 N Min 20 N
Note: <ol style="list-style-type: none"> 1. Must be a pass report. 2. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. 3. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. 4. Reports combined tested at different times and different sample will be considered as failure. 5. Test that are not requested would not need any report. 6. Report must be authentic and would be counter checked as Nepal Police's discretion. 7. Any report found fake or is not in the system would be considered as Spam thus failure. <p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

WOOLEN SWEATER (उनी जर्सी)

Details	Specification
a) Color	Color as per sample of Nepal Police.
b) Fiber Content <ul style="list-style-type: none"> Acrylic Wool Nylon 	67 % (± 2) 22 % (± 2) 11 % (± 2)
c) Color Fastness to rubbing <ul style="list-style-type: none"> Dry Wet 	Min 4 Min 4-5
d) Color Fastness to washing Warm Water Temperature $40^0 \pm 5^0$ cool iron	Min 4
e) Construction <ul style="list-style-type: none"> Wales Course 	5 per inch (± 1) 14 per inch (± 1)
f) Total Weight	630 gram (± 75)
g) Color fastness to light Color Change (After 40 AFU):	Min 4
h) Pilling Resistance (Random after 30minutes):	Min 4
<u>Note:</u> <ol style="list-style-type: none"> Must be a pass report. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. Reports combined tested at different times and different sample will be considered as failure. Test that are not requested would not need any report. Report must be authentic and would be counter checked as Nepal Police's discretion. Any report found fake or is not in the system would be considered as Spam thus failure.	
Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time. TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.	

WOOLEN BLANKET (उनी कम्बल)

Details	Specification
Color	Color as per sample of Nepal Police
a) Fiber Content <ul style="list-style-type: none"> Wool Acrylic Other Fibers 	70 % (± 3) 15 % (± 3) Rest
b) Total Weight	2510 gram (± 100)
c) <u>Border of Blanket</u> <ul style="list-style-type: none"> Fabric of the Border of Blanket: Polyester Width of the Fabric at the Border (Both side) 	100% 3.0 cm (± 0.5)
d) Size of Blanket <ul style="list-style-type: none"> Length: Width: 	235 cm (± 5) 155 cm (± 5)
<u>Note:</u> <ol style="list-style-type: none"> Must be a pass report. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. Reports combined tested at different times and different sample will be considered as failure. Test that are not requested would not need any report. Report must be authentic and would be counter checked as Nepal Police's discretion. Any report found fake or is not in the system would be considered as Spam thus failure. 	
Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.	
TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.	

DMS BOOTS (डि.एम.एस. बुट)

Height	9 to 9.5 inches from the bottom of the sole
Eyelets	9 pairs of eyelets (there should not be any raw edges to avoid damage to the lace)
Upper	Genuine leather, breathable (Soft feel) embossed body, plain on toe and heel cover 1.8mm or above leather.
Lining	Black color soft natural genuine leather lining ,breathable and flexible, sweat absorption
Tongue	Genuine leather up to the top with leather lining laminated with sponge. Attached to the main body to protect from water height up to 6"
Help loop	Genuine leather loop with thickness:- 1.8mm or above
COLLAR	BLACK LEATHER, SOFT WITH SPONGE INSERT FOR SOFT FEEL.
Lace	Black color ,length not less than 160cm
Thickness of vamp	Not less than 1.8mm
Thickness of quarter	Not less than 1.8mm
Thickness of counter	Not less than 1.8mm
Thickness of tongue	Not less than 1.4mm
Thickness of outsole	Toe: 20mm-25mm (Including uplift at the front as per Nepal police sample) Middle :18mm-23mm (As per Nepal police sample) Heel :40mm-47mm(including the uplift at the back of the heel as per Nepal police sample) Sole Grips must be as per Nepal police sample or similar standard
Feet bed	Removable EVA with mesh clothing ,washable
Outsole	Rubber not less than 98% With <ul style="list-style-type: none"> a. Hardness:ASTMD 2240:65(+5) b. Flexing Endurance c. Abrasion resistance d. Non-Marking e. Static Skid Resistance
Design	As per Nepal Police There should be no shade, or/and different thickness of leather used unless otherwise specified by Nepal police. Must be Genuine leather on top With specified details as per this chart Toe:Round finish, no over raised

Whole boot	Black color Size: 3-13 Weight: Around 1.5kg/pair (8 size) or more a. Seam strength b. Aging test
TESTREPORT REQUIRMENTS	TEST REQUIRMENTS AND STANDARD
<p><u>LAB TEST based on AATCC STANDARD NEEDED either from SGS or ITS where ever AATCC is not applicable may use ASTM standard unless otherwise listed specifically</u></p> <ol style="list-style-type: none"> 1. Must be a pass report. 2. It can be better than the current request 3. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. 4. Report must be from single fabric/sample. 5. Reports combined tested at different times and different sample will be considered as failure. 6. Test that are not requested would not need any report. 7. Report must be authentic and would be counter checked as Nepal Police's discretion. 8. Any report found fake or is not in the system would be considered as Spam thus failure. 	<p><u>Lab Report to supply with the bidding sample</u></p> <ol style="list-style-type: none"> 1. UPPER <ul style="list-style-type: none"> • Tear Strength should be not less than 35kgs per square cm minimum of 10kgs with reinforcements • Leather confirmation test: to confirm the upper leather thickness and leather type. • Bursting strength: should be no less than 35kgs per square cm • Flexing Resistance: No damage to surface at room temperature after 50,000flexs, for cold (10degree Celsius): should be 20,000flexs. • Crocking: Rubbing: Dry 3.5equal or better, Wet 3 or better at 10 rubs • Water resistance: good at 15,000flex • Water Repellent: 80-wetting of material surface at spray point required 2. TONGUE <ul style="list-style-type: none"> • Seam strength More or equal to 25kg per square cm 3. Help Loop <ul style="list-style-type: none"> • post attachment strength must be more or equal to 25kgs per cm 4. Thickness of Vamp, Thickness of quarter, thickness of counter, Thickness of tongue, must be not less than 1.8mm leather 5. SOLE (Rubber) <ul style="list-style-type: none"> • Outer sole: must be within this parameters (designed as per Nepal police sample. Toe: 20mm-27mm (Including uplift at the front as per Nepal police sample) • Middle :18mm-25mm (As per Nepal police sample) • Heel :40mm-47mm (including the uplift at the back of the heel as per Nepal police sample) • Sole Grips must be as per Nepal police sample or similar standard • Must be confirmed Rubber with following test as well • Hardness ASTM:2240656(+5)

	<ul style="list-style-type: none"> • Flexing endurance: no crocking after 50,000 flexes • Abrasion resistance: Every day 250mm cubic maximum • No Marking: no worse than slight marking after cleaning (3 grades) • Static skid resistance: dry 0.7 and wet 0.3 or better
	<p>6. WHOLE BOOT</p> <ul style="list-style-type: none"> • Seam strength: more or equal to 25kg per square cm • Aging Test: no changes of color or finishing after 60 degree Celsius for 5dys
<p>Further below is the physical standard that would be considered when the production goods are received. Nepal police may hire an expert or Nepal police themselves will do the inspection as needed.</p> <p>Randomly pick samples from production: can be sent to SGS or ITS anytime. If the production does not match the standard, then shipment can be rejected at any time.</p>	

Ruksag Bag (रुकस्याग झोला)

Details	Specification
a) Color	Color as per sample of Nepal Police
b) Total weight of bag (g)	2075 gram (± 100)
c) Color Fastness to Water <ul style="list-style-type: none"> Net Patch Outer Fabric 	Min 4-5 Min 4-5
d) Size Measurements <u>Front Pocket</u> <ul style="list-style-type: none"> Length Width Height 	25 cm (± 1.5) 5.5 cm (± 1) 31.5 cm (± 1.5)
e) Size Measurements <u>Only Main Body</u> <ul style="list-style-type: none"> Length Width Height 	31 cm (± 1.5) 29.5 cm (± 1.5) 68 cm (± 1.5)
f) Fiber Content <u>Base</u> <ul style="list-style-type: none"> Polyester <u>Lining</u> <ul style="list-style-type: none"> Polyester 	Min 98% Min 98%
g) Seam Strength (Grab Test) <u>Outer Fabric</u> <ul style="list-style-type: none"> Side Seam Bottom Length Seam Bottom Width Seam (Double Seam) <u>(Seam with different Fabric)</u> <ul style="list-style-type: none"> Side Seam Bottom Width 	Min 500 N Min 400 N Min 780 N Min 410 N Min 560 N
<p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed.</p> <p>Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

PARKA JACKET (पार्का ज्याकेट)

Details	Specification
a) <u>Fiber Content</u> <ul style="list-style-type: none"> Inner Fabric (Polyester) Lining Fabric (Polyester) <u>Outer Fabric</u> <ul style="list-style-type: none"> Polyester Viscose <u>Fur Fabric</u> <ul style="list-style-type: none"> Polyester 	Min 98% Min 98% 60 % (± 3) 40 % (± 3) Min 98%
b) Construction (outer fabric) <ul style="list-style-type: none"> Ends Picks 	418 (± 5) per 10 cm 180 (± 5) per 10 cm
c) Color	Color as per sample of Nepal Police
d) GSM <ul style="list-style-type: none"> Fur Fabric Inner Filling Material Lining Fabric Outer Fabric 	379 g/m ² (± 10) 59 g/m ² (± 2) 55 g/m ² (± 2) 319 g/m ² (± 5)
e) Total Weight	1350 gram (± 100)
f) Weight of detachable	300 gram (± 25)
g) color fastness to washing (outer Fabric) Warm Water Temperature 40 ⁰ ± 5 ⁰ cool iron	Min 4
h) Color Fastness to Rubbing(Outer Fabric): <ul style="list-style-type: none"> Dry Wet 	Min 4-5 Min 2-3
i) Tear strength (Outer Fabric) <ul style="list-style-type: none"> Length Width 	Min 48 N Min 48 N
j) Pilling (Outer Fabric) after 30 min	Min 4
a) Seam Strength (Grab Test) <u>Outer Fabric</u> <ul style="list-style-type: none"> Shoulder Seam (Double Seam) Side Seam (Double Seam) Sleeve Seam (Double Seam) Arm Seam (Double Seam) Sleeve Length Arm Hole Width 	Min 300 N Min 380 N Min 400 N Min 300 N Min 400 N Min 160 N
Note: <ol style="list-style-type: none"> Must be a pass report. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. 	

क्रमशः

3. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report.
4. Reports combined tested at different times and different sample will be considered as failure.
5. Test that are not requested would not need any report.
6. Report must be authentic and would be counter checked as Nepal Police's discretion.
7. Any report found fake or is not in the system would be considered as Spam thus failure.

Nepal police may hire an expert or Nepal police themselves will do the inspection as needed.
Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.

TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.

Sleeping Bag (स्लिपिड व्याग)

Details	Specification
1. Total Weight of Sleeping bag with Carry Bag	1232 Grams (± 50 Grams)
2. Weight of Carry Bag	115 Grams (± 15 Grams)
3. <u>Carry Bag Fabric</u> a. Fiber Content b. Weight per Unit Area	100% Nylon 126 (± 5) g/m ²
4. <u>Sleeping Bag outer Fabric</u> a. Fiber Content b. Weight Per Unit Area c. Color Fastness to Rubbing Dry Wet d. Color Fastness to Light (Xenon Arc) (Grey Scale) Colour Change (After 40 AFU) e. Tear Strength Warp Weft f. Tensile Strength (1 Inch Grab) Warp Weft g. Construction : Warp per 10 cm Weft per 10 cm	100% Polyester 73 (± 2) g/m ² Minimum 4/5 Minimum 4/5 Minimum 3.5 Minimum 15 N Minimum 9.5 N Minimum 600 N Minimum 300 N 621 (± 5) 348 (± 5)
5. <u>Sleeping Bag Inner Fabric</u> a. Fiber Content b. Weight Per Unit Area c. Color Fastness to Rubbing Dry Wet d. Color Fastness to Light (Xenon Arc) (Grey Scale) Colour Change (After 40 AFU) e. Tear Strength Warp Weft f. Tensile Strength (1 Inch Grab) Warp Weft	100% Polyester 79 (± 2) g/m ² Minimum 4/5 Minimum 4/5 Minimum 3.5 Minimum 11 N Minimum 8 N Minimum 510 N Minimum 360 N
6. <u>Dimension of Sleeping Bag</u> a. Length from back side, all the way to hood b. Length front part from Throat to bottom c. Width	229 cm (± 3 cm) 197 cm (± 3 cm) 139 cm (± 3 cm)
<p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

RAIN COAT SET (रेन सुट)

Details	Specification
a) Color	Color as per Sample of Nepal Police
b) Total Weight <ul style="list-style-type: none"> • Top • Bottom 	800 gram (± 50) 550 gram (± 50)
c) Fiber Content (Outer Fabric) Nylon	Min 98%
d) GSM (Outer Fabric)	236 g/m ² (± 5)
e) Color Fastness to Rubbing (Outer Fabric) Dry Wet	Min 4 Min 4-5
f) Color Fastness to Water (Outer Fabric)	Min 4-5
g) Color Fastness to Light (Outer Fabric) Color Change (After 40AFU):	Min 4
h) Water Repellency:	Min 2
i) Tear Strength (Outer Fabric) Length Width	Min 48 N Min 24 N
j) Seam Strength (Grab Test) <u>Outer Fabric</u> <ul style="list-style-type: none"> • Side Seam • Sleeve Seam • Width Seam • Hood Length (Double Seam) • Hood Width (Double Seam) 	Min 230 N Min 280 N Min 260 N Min 250 N Min 210 N
<u>Note:</u> <ol style="list-style-type: none"> 1. Must be a pass report. 2. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. 3. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. 4. Reports combined tested at different times and different sample will be considered as failure. 5. Test that are not requested would not need any report. 6. Report must be authentic and would be counter checked as Nepal Police's discretion. 7. Any report found fake or is not in the system would be considered as Spam thus failure. <p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

BERET CAP(ब्यारेट क्याप)

Details	Specification
a) Color	Color as per sample of Nepal Police
b) Fiber Content <ul style="list-style-type: none"> Inner Fabric (Polyester) Outer Fabric (Wool) 	100 % 100 %
c) Color Fastness to Rubbing <u>Outer Fabric</u> <ul style="list-style-type: none"> Dry Wet 	Min 4 Min 4
d) Total Weight	100 gram (±5)
e) Color fastness to light Color change (after 40 AFU) <ul style="list-style-type: none"> Outer Fabric 	Min 4
<p>Note:</p> <ol style="list-style-type: none"> Must be a pass report. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. Reports combined tested at different times and different sample will be considered as failure. Test that are not requested would not need any report. Report must be authentic and would be counter checked as Nepal Police's discretion. Any report found fake or is not in the system would be considered as Spam thus failure. <p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

P.T. SHOES (पि.टी. जुता)

Details	Specification
a) Color	Color as per sample of Nepal Police
b) Flexing Resistance Cut growth (after 30,000 flexes)	± 1.0 mm
c) Color Fastness to rubbing <u>Lace:</u> Dry Wet <u>Outer Fabric:</u> Dry Wet	Min 4 Min 4 Min 4 Min 3-4
d) Fiber Content <u>Lace:</u> Polyester <u>Upper Fabric</u> Cotton:	100% 100 %
e) Total height of shoes from back side	15 cm (± 2)
f) Abrasion Resistance <ul style="list-style-type: none"> Density Relative Volume Loss 	1.15 mg/mm ³ (± 0.1 mg/ mm ³) Maximum 150 mm ³
<u>Note:</u> <ol style="list-style-type: none"> Must be a pass report. If a single test result does not meet standard requested, the goods will be considered as fail not to the standard. Report must be from single sample and components used to make the exact products for the samples. Product should match the test report. Reports combined tested at different times and different sample will be considered as failure. Test that are not requested would not need any report. Report must be authentic and would be counter checked as Nepal Police's discretion. Any report found fake or is not in the system would be considered as Spam thus failure. <p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

Under Trouser Vest Set (अण्डर ट्राउजर भेष्ट सेट)

Details	Specification
a) Color	Color as per sample of Nepal Police
b) Total Weight	630 gram (± 50)
c) Fiber Content	Polyester: 54 % (± 3) Cotton: 46 % (± 3)
d) Color Fastness to Rubbing	Dry : Min 4-5 Wet : Min 3-4
e) Construction	Wales: 32 per inch (± 2) Course: 36 per inch (± 2)
f) Color fastness to light Color change (after 40 AFU)	Min 2.5
<p>Nepal police may hire an expert or Nepal police themselves will do the inspection as needed. Randomly pick samples from production: can be sent for testing anytime. If the production does not match the standard then shipment can be rejected at any time.</p> <p>TEST METHOD FOR THE ABOVE PARAMETERS SHOULD BE BASED ON RELEVANT ISO OR ASTM OR OTHER INTERNATIONAL STANDARDS.</p>	

Mosquito Net (झुल)

Details	Specification
1. Weight	550 gm. Minimum
2. Dimensions	Length :- 210 (± 3) cm
	Width :- 110 (± 3) cm
	Height without Sheeting Boarder :- 150 (± 3) cm
	Height of Sheeting Boarder :- 30 (± 3) cm
3. Mesh	(Square Per Inch) :- 255 (± 25)
4. Material Type	Net :- Min 98% Polyester <u>Sheeting Fabric</u> Polyester: 80% (± 5) Cotton/Viscose: 20% (± 5)
5. Shape of hole	The shape of the hole of net should be hexagonal.
6. Color and design	Sky Blue in color and design should be as per sample of Nepal Police.